

ION CONDUCTIVE ROLLER AND IMAGE FORMING APPARATUS
EMPLOYING ION CONDUCTIVE ROLLER

FIELD OF THE INVENTION AND RELATED ART

5 The present invention relates to an image forming apparatus such as a printer, a copying machine, a facsimileing machine, etc. In particular, it relates to an apparatus employing an ion conductive roller.

10 An image forming apparatus such as an electrophotographic copying machine, a laser beam printer, etc., employs an electrophotographic photosensitive member (which hereinafter will be referred to simply as photosensitive drum), and a
15 plurality of processing means such as a charging means, an exposing means, and a developing means, to form a toner image, as a transferable image, in accordance with image formation data. The toner image is transferred onto transfer medium with the use of a
20 transferring means. Then, the transfer medium is introduced into a fixing means, in which the toner image is thermally fixed to the surface of the transfer medium, becoming a permanent image. After the fixation of the toner image, the transfer medium
25 is outputted as a finished product (copy, print).

 After the transfer of the toner image onto the transfer medium, the photosensitive drum is

cleaned; the residues such as the toner particles,
paper dust, etc., remaining on the peripheral surface
of the photosensitive drum are removed. Then, the
photosensitive drum is used again for an image
5 formation process; it is repeatedly used for an image
formation process.

Before the photosensitive drum is exposed,
the entire range of the photosensitive drum in terms
of its lengthwise direction is charged. As the means
10 for charging the photosensitive drum, those employing
a charge roller have come to be widely used in recent
years. A charge roller is placed in contact with a
photosensitive drum; it is a contact type charging
member. As voltage is applied to the charge roller in
15 contact with the photosensitive drum, the
photosensitive drum is electrostatically charged in
the charging station, or the contact area between the
peripheral surfaces of the photosensitive drum and
charge roller.

20 As for the means for transferring a toner
image from a photosensitive drum, a transferring means
employing a so-called transfer roller, which is of a
rotational contact type, has come to be widely used
because of its advantage that not only can the
25 employment of a transfer roller simplify the transfer
medium conveyance path, but also it can stabilize the
transfer medium conveyance. The transfer roller is

placed in contact with the photosensitive drum,
forming the transfer medium nipping portion, or
transfer station, between the peripheral surfaces of
the transfer roller and photosensitive drum. In
5 operation, transfer medium is conveyed through the
transfer station while voltage is applied to the
transfer roller, so that a toner image on the
peripheral surface of the photosensitive drum is
electrostatically transferred onto the transfer
10 medium. The charge roller and transfer roller are
both for charging objects, that is, photosensitive
drum and transfer medium, respectively, and are
electrically conductive.

Referring to Figure 9, one of the recently
15 proposed transfer rollers 116 comprises an
electrically conductive metallic core 117, and an
elastic and electrically conductive layer formed in a
manner to wrap the peripheral surface of the metallic
core 117. Transfer rollers 116 can be roughly divided
20 into two types based on whether a transfer roller 116
is conductive of electrons or ions: (1) electron
conductive type and (2) ion conductive type.

Referring to Figure 9, an electron conductive
transfer roller (1) is provided with an elastic layer
25 118, in which electrically conductive filler has been
dispersed. For example, there is an electron
conductive roller, in the elastic layer of which

electrically conductive filler such as carbon, metallic oxide, etc., has been dispersed.

Also referring to Figure 9, an ion conductive transfer roller (2) is provided with an elastic layer 118 which contains ion conductive substance(s). For example, there are an ion conductive roller, the elastic layer itself of which is formed of ion conductive substance such as urethane, and an ion conductive roller, in the elastic layer of which surfactant has been dispersed.

The electrical conductivity of an electrically conductive roller of the electron conductive type comes from the electrically conductive filler dispersed in the elastic layer of the roller as described above. Therefore, it has the following problem. That is, when manufacturing an electron conductive roller, its elastic layer becomes uneven in electrical resistance due to the deformation or the like of the elastic layer which occurs as its metallic core is pressed into the elastic layer. Therefore, it is rather difficult to manufacture an electron conductive roller which is uniform in electrical conductivity. This problem is difficult to eliminate, and limits the usage of an electrically conductive roller of the electron conductive type as a charge roller or transfer roller for an image forming apparatus. If the unevenness in electrical resistance

of the elastic layer of an electrically conductive roller is substantial, the roller becomes uneven in the amount of the electrical current which flows through the roller, in terms of the lengthwise
5 direction of the roller as well as the rotational direction of the roller, causing some areas of the photosensitive drum to be overcharged, whereas other areas are undercharged. Further, sometimes, the electrical current is concentrated to the areas of
10 minuscule size, of the peripheral surface of the photosensitive drum, by the electrical discharge caused by the bias applied to the roller. Such concentration of electrical current leaves traces of electrical discharge, which sometimes results in the
15 formation of an inferior image.

In comparison, the problem that electrical discharge concentrates to minuscule areas of the peripheral surface of a photosensitive drum is not suffered from by a transfer roller of the ion
20 conductive type, because of the characteristics of a transfer roller of the ion conductive type in terms of electrical conductivity. Further, the elastic layer of the transfer roller of the ion conductive type is not likely to become uneven in electrical resistance
25 even if it is deformed. In other words, an electrically conductive roller of the ion conductive type is superior to an electrically conductive roller

of the electron conductive roller type in that the former is capable of more uniformly charging an object than the latter. Therefore, the employment of the former has been increasing in the recent years.

5 The employment of an ion conductive roller, however, has more frequently resulted in the so-called drum contamination by seepage, that is, the problem that a photosensitive drum is contaminated by the seepage from electrically conductive rollers. This
10 problem is thought to occur because the addition of ion conductive substances enhances the seepage and/or the rubbery substances preferable as the material for an ion conductive roller tend to allow the seepage. Thus, as an ion conductive roller is placed in contact
15 with a moving object, the seepage from the roller formed film of the seepage on the surface of the moving object, adversely affecting the condition under which the moving object is charged. For example, when the object with which an ion conductive roller is
20 placed in contact is a photosensitive drum, the seepage from the ion conductive roller contaminates the peripheral surface of the photosensitive drum, changing thereby the surface properties of the photosensitive drum. As a result, it becomes
25 impossible to form an image of good quality. This is the problem from which an ion conductive roller in accordance with the prior art has been suffering.

SUMMARY OF THE INVENTION

An object of the present invention is to prevent the ingredients of an ion conductive roller
5 from seeping out of the roller.

Another object of the present invention is to provide an image forming apparatus employing an ion conductive roller from which the ingredients thereof do not seep out.

10 Another object of the present invention is to provide an image forming apparatus comprising a movable member, and a roller which is placed in contact with said movable member as necessary, or always kept in contact with said movable member, said
15 roller comprising an elastic layer to be placed in contact with said movable member, and said elastic layer being ion conductive, no less than 20° and no more than 50° in hardness (hardness is measured while
20 by applying 500 g of weight on a 4.0 mm thick piece of elastic layer cut from roller, and expressed in Asker-C scale), and no less than 65 in the "hardness/specific gravity (g/cm^3)" ratio.

Another object of the present invention is to provide a roller, the elastic surface layer of which
25 is ion conductive, no less than 20° and no more than 50° in hardness, the hardness and specific gravity (g/cm^3) of which satisfies the following inequality:

hardness/specific gravity ≥ 65 (hardness is measured while applying 500 g of weight on a 4.0 mm thick piece of elastic layer cut from roller, and expressed in Asker-C scale).

5 These and other objects, features, and advantages of the present invention will become more apparent upon consideration of the following description of the preferred embodiments of the present invention, taken in conjunction with the
10 accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a perspective view of an ion conductive roller similar to the ion conductive
15 rollers in the first to seventh embodiments of the present invention.

Figure 2 is a schematic sectional view of an image forming apparatus with which the ion conductive rollers in the first to fifth embodiments of the
20 present invention are used.

Figure 3 is a schematic sectional view of the transfer roller in the first embodiment of the present invention, parallel to the axial direction of the roller, showing only the lengthwise ends thereof.

25 Figure 4 is a schematic cross section of one of the lengthwise end portions of the transfer roller in the first embodiment of the present invention.

Figure 5 is a schematic drawing showing a method for measuring the electrical resistance of an ion conductive roller in accordance with the present invention.

5 Figure 6 is a graph showing the results of the drum contamination test carried out to find out the relationship between the "hardness/specific gravity" ratio of a transfer roller in accordance with the present invention, and the extent of the
10 photosensitive drum contamination by the transfer roller.

Figure 7 is a schematic sectional view of the image forming apparatus in the sixth embodiment of the present invention.

15 Figure 8 is a schematic sectional view of the image forming apparatus in the seventh embodiment of the present invention.

Figure 9 is a perspective view of a typical electrically conductive roller in accordance with the
20 prior art.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Hereinafter, the preferred embodiments of the present invention will be described in detail with
25 reference to the appended drawings.

(Embodiment 1)

Referring to Figures 1 - 6, the first

embodiment of the present invention will be described.

This embodiment is characterized in that an ion conductive roller is used as a transfer roller.

[Image Forming Apparatus]

5 First, the image forming apparatus in this embodiment will be roughly described with reference to Figure 2, which is a schematic sectional view of the image forming apparatus in this embodiment, showing the general structure thereof.

10 Referring to Figure 2, in the adjacencies of the peripheral surface of a photosensitive drum 1 as an image bearing moving object, a charge roller 2, an exposing apparatus (laser scanner) 3, a developing apparatus 4, a transfer roller 5, a fixing apparatus
15 6, and a cleaning apparatus 7 are disposed in a manner to surround the photosensitive drum 1.

The photosensitive drum 1 is 24 mm in diameter, and comprises a cylindrical substrate formed of aluminum, nickel, or the like, and a layer of
20 photosensitive substance, such as amorphous silicon, coated on the peripheral surface of the cylindrical substrate. It is rotationally driven (moved) at a predetermined process speed.

The charge roller 2 is kept pressed on the
25 photosensitive drum 2 with the application of a predetermined amount of pressure so that the peripheral surface of the charge roller 2 is kept in

contact with the peripheral surface of the
photosensitive drum 1. Thus, the charge roller 2 is
rotated by the rotation of the photosensitive drum 1.
As a predetermined amount of charge bias is applied to
5 the charge roller 2 from a charge bias power source
(unshown) while the charge roller 2 is rotated in
contact with the photosensitive drum 1, the
photosensitive drum 1 is charged to predetermined
polarity and potential level.

10 The exposing apparatus 3 forms an
electrostatic latent image on the photosensitive drum
1 by exposing the charged photosensitive drum 1 to a
beam of laser light L, which the exposing apparatus 3
emits in accordance with the image formation data
15 inputted into the exposing apparatus 3.

The developing apparatus 4 in this embodiment
is of a reversal development type. It has a
development sleeve 4a, to which development bias is
applied from a development bias power source
20 (unshown).

The transfer roller 5 as a contact
transferring means comprises a metallic core, and a
spongy elastic layer formed on the peripheral surface
of the metallic core. To the transfer roller 5,
25 transfer bias is applied from a transfer bias power
source (unshown). The details of the structure of the
transfer roller 5 will be described later.

[Image Formation Method]

Next, the image forming operation of the above described image forming apparatus will be described.

5 During image formation, the photosensitive drum 1 is rotationally driven at a predetermined process speed by a driving means (unshown). While the photosensitive drum 1 is rotationally driven, its peripheral surface is charged by applying charge bias
10 to the charge roller 2 from the charge bias power source (unshown).

 The charge peripheral surface of the photosensitive drum 1 is exposed to the scanning beam of laser light L projected while being turned on or
15 off in accordance with image formation data. As a result, an electrostatic latent image is formed on the peripheral surface of the photosensitive drum 1.

 The electrostatic latent image is developed by the developing apparatus 4; it is turned into a
20 toner image, that is, a visible image.

 Meanwhile, a single or a plurality of transfer mediums P, such as a piece of recording paper, as movable objects are fed one by one by a sheet feeding roller 12 or 13 into the main assembly
25 of the image forming apparatus from a manual feed tray 10 or a cassette 11, respectively. After being fed into the main assembly and having come into contact

with a pair of registration rollers 16 by the leading edge, the transfer medium P is kept on standby by the registration roller 16, with the leading edge remaining in contact with the registration rollers 16, until it is detected by a pre-feed sensor 14 that the temperature of the fixing apparatus has reached the fixation temperature. As the temperature of the fixing apparatus reaches the fixation temperature, the transfer medium P is released by the registration rollers 16 in synchronism with the formation of the toner image on the peripheral surface of the photosensitive drum 1, and is delivered to the transfer nip (transfer station), the nipping portion formed between the photosensitive drum 1 and transfer roller 5, while being guided by a pre-transfer guide 17. The transfer roller 5 is being supplied with the bias from the unshown power source. The transfer roller 5 is kept pressed on the photosensitive drum 1 by the application of pressure equivalent to 500 g of weight. The transfer of the toner image onto the transfer medium P is caused by charging the transfer medium P by the transfer roller 5.

While the transfer medium P is moved through the transfer nip, the toner image on the peripheral surface of the photosensitive drum 1 is transferred onto the transfer medium P. After the transfer of the toner image onto the transfer medium P, the transfer

medium P is conveyed to the fixing apparatus 6. In the fixing apparatus 6, the transfer medium P and the toner image thereon are subjected to heat and pressure in the transfer nip of the fixing apparatus 6. As a
5 result, the toner image is permanently fixed to the transfer medium P. Then, the transfer medium P is discharged from the main assembly of the image forming apparatus.

Meanwhile, the transfer residual toner
10 particles, that is, the toner particles remaining on the peripheral surface of the photosensitive drum 1 after the toner image transfer, are removed from the peripheral surface of the photosensitive drum 1 by the cleaning apparatus 7.

15 [Ion Conductive Roller]

Next, the transfer roller 5, which is an ion conductive roller, will be described.

The transfer roller 5 looks like the roller, shown in Figure 1 which is a perspective view of the
20 ion conductive roller 111 in accordance with the present invention (ion conductive rollers in the following embodiments also look roughly the same). It comprises an electrically conductive metallic core 112, and an elastic cylindrical layer 113 fitted
25 around the peripheral surface of the metallic core 112. The elastic layer is given electrical conductivity. In this embodiment of the present

invention, the elastic layer 113 is ion conductive, being therefore less nonuniform in terms of electrical resistance. Therefore, it is superior to an electron conductive roller in that the former is capable of
5 more uniformly charging an object than the latter. Referring to Figure 3, the metallic core 5a of the transfer roller 5 is formed of iron, stainless steel, aluminum, or the like. The elastic layer 5b of the transfer roller 5 is in the form of a hollow cylinder,
10 and is formed of a spongy substance formed of EPDM (ethylene propylene rubber), NBR (acrylonitrile butadiene rubber), ECO (epichlorohydrin-ethylene oxide rubber), or the like. As the material for the elastic layer 5b in this embodiment, an elastic substance, the
15 hardness of which measured while it is under 500 g of weight is in the range of 20° - 50° on the Asker-C hardness scale (Type C Rubber Hardness Gauge made by Koobunshi Keiki Co.), and the electrical resistance of which is in the range of 10^6 - 10^{10} Ω , is used.

20 Incidentally, the hardness value of the elastic layer of each of the electrically conductive rollers in all the embodiments of the present invention was measured with the use of a Rubber Hardness Gauge C (product of Koobunshi Keiki Co.)
25 while the elastic layer was kept under 500 g of weight (inclusive of weight of measuring instrument itself), and is expressed on the Asker-C scale. More

specifically, a piece of the elastic layer portion of the ion conductive roller was cut out so that the thickness of the piece became 4.0 mm. Then, the piece was placed on a plate made of steel or the like, and the hardness of the piece was measured. It was assured that when cutting out a piece of the elastic layer to measure the hardness of the elastic layer, the area of the cut piece within 10 mm radius from the point of the cut piece with which the probe is placed in contact, became 4.0 mm in thickness. In the case of a roller, the elastic layer of which is 4.0 mm in thickness, the value obtained by measuring the hardness of the elastic layer of this roller without cutting a piece out of the elastic layer sometimes is the same as the value obtained by measuring the hardness of a piece of the elastic layer cut out of the elastic layer of the roller. In such a case, the hardness of the elastic layer of the roller may be directly measured after confirming the relationship between the value obtained by directly measuring the hardness of the elastic layer of the roller, that is, without cutting out a piece of the elastic layer. However, when measuring the hardness of the elastic layer of a roller formed by pressing the metallic core portion of the roller into the elastic layer portion of the roller, special attention should be paid for the following reason. That is, after the insertion of

the metallic core into the elastic layer portion, the elastic layer portion is in the compressed condition. Therefore, in the case of some rollers, the value obtained by measuring the hardness of the elastic layer while the elastic layer is on the metallic core are different from the value obtained by measuring the test piece cut out of the elastic layer on the metallic core. When it is impossible to obtain a test piece having the thickness of 4.0 mm, the value obtained by measuring the hardness of the combination of two 2.0 mm thick test pieces placed in layers may be substituted for the value of the hardness of a 4.0 mm thick test piece, as long as the elastic layer is uniform in physical properties in terms of the thickness direction of the elastic layer. It has been confirmed by the inventors of the present invention that such substitution did not substantially affect the results of the measurements.

A simplified version of the method for forming the elastic layer 5b is as follows. First, such chemicals as vulcanizing agent, filler, foaming agent, vulcanization accelerator, foaming accelerator, etc., are added to such rubber as EPDM, NBR, ECO, etc. Then, the mixture is kneaded. Then, the kneaded mixture is extruded to form the cylindrical elastic layer portion of a roller. The vulcanization accelerator is preferably thiuram type vulcanization

accelerator, since then a great amount of sulfur is supplied. Then, the formed cylindrical elastic layer portion of a roller is subjected to first and second curing processes. Then, a metallic core is pressed
5 into the center hole of the cured elastic layer portion of a roller. Lastly, the surface of the roller is polished to complete a roller having a predetermined shape and measurements.

Referring to Figure 3, the transfer roller 5
10 is disposed in parallel to the photosensitive drum 1, and is rotatably supported by a pair of bearings 5c by the lengthwise end portions, one for one, of the metallic core 5a of the roller 5. The transfer roller 5 is kept pressured by a total pressure equivalent to
15 1.0 kg of weight generated by a pair of compression springs 5d, upon the photosensitive drum 1 so that a transfer nip N is formed between the peripheral surfaces of the elastic layer 5b and photosensitive drum 1.

20 The gear 5e in Figure 3 is fixed to one of the lengthwise ends of the metallic core 5a of the transfer roller 5, and is meshed with an unshown driving gear. Thus, rotational force is transmitted from the unshown driving gear to the gear 5e, rotating
25 thereby the transfer roller 5 in the counterclockwise direction indicated by an arrow mark *b* in Figure 4 at a predetermined peripheral speed. On the other hand,

the photosensitive drum 1 is rotationally driven in the clockwise direction indicated by an arrow mark a shown in Figure 4 at a predetermined peripheral velocity. The transfer medium P is conveyed in the direction indicated by an arrow mark c in Figure 4, and is delivered to the transfer nip N formed by the photosensitive drum 1 and transfer roller 5, while being guided by the pre-transfer guide 17.

To the transfer roller 5, transfer bias is applied from a transfer bias application power source 21 through the pair of compression springs 5d, pair of bearings 5c, and metallic core 5a, which are electrically conductive.

While the transfer medium P having been delivered to the transfer nip N with a predetermined control timing is conveyed through the transfer nip N while remaining nipped by the photosensitive drum 1 and transfer roller 5, the predetermined voltage opposite in polarity to the toner image on the photosensitive drum 1 is applied to the transfer roller 5 from the transfer bias application power source 21. As a result, the transfer medium P is electrically charged in the transfer nip N, causing thereby the toner image on the photosensitive drum 1 to be electrostatically transferred onto the transfer medium P as if the toner image were rolled out of the photosensitive drum 1 onto the transfer medium P.

The method for measuring the electrical resistance of the transfer roller 5 is as follows. Referring to Figure 5, the transfer roller 5 is placed in contact with an aluminum cylinder so that a total
5 contact pressure of 600 g (300 g per lengthwise end) is maintained between the photosensitive drum 1 and transfer roller 5. Then, the maximum and minimum amounts of the voltage between the two ends of a resistor 75 are read with the use of a voltmeter 73
10 when a certain amount of voltage (for example, +2.0 kV) is applied while the transfer roller 5 is rotated. Then, the average value of the electrical current which flows through the circuit is calculated from the voltage values. Then, from the average current value,
15 the electrical resistance of the transfer roller 5 is calculated (measurement conditions: 20°C in temperature and 60 % in relative humidity).

The transfer roller 5 in this embodiment is a transfer roller having a spongy elastic layer, the
20 hardness of which is in the range of 20° - 50°, which is the desirable range for the transfer roller 5 to be used as a transfer roller for an image forming apparatus. It is formed of the material concocted so that the value of "hardness/specific gravity" ratio of
25 the entirety of the elastic layer 5b of the transfer roller 5 becomes no less than 65, without hardening the surface thereof, that is, without exposing it to

ultraviolet rays or the like to change the elastic layer in cross-linking density.

The studies made by the inventors of the present invention revealed that the specific gravity and hardness of the elastic layer of a transfer roller, and the ratio of the hardness to the specific gravity, seriously affect the seepage from the transfer roller, and also that the greater the amount of the seepage, the greater the possibility that the photosensitive drum will be contaminated. Thus, in order to prevent the photosensitive drum contamination traceable to the seepage from a transfer roller, the inventors of the present invention carried out various experiments in which the choice of material for the elastic layer of a transfer roller, combination among the materials, manufacturing conditions, etc., were varied. The experiments revealed that as long as a transfer roller was manufactured so that its elastic layer 5b became no less than 50 in "hardness/specific gravity" ratio, the problem that the photosensitive drum 1 is contaminated by a transfer roller 5 could be prevented.

The experiment also revealed that as long as a transfer roller was manufactured under appropriate conditions, by choosing and combining the materials for a transfer roller 5 so that the elastic layer 5b of a transfer roller 5 became no less than 65 in

"hardness/specific gravity" ratio, the amount by which the peripheral surface of the transfer roller was frictionally worn was smaller, and therefore, the roller remained stable in performance.

5 [Seepage]

[Results of Experiments]

(Amount of Sulfur)

A plurality of ion conductive rollers comprising a metallic core with an external diameter of 6 mm, and a spongy elastic layer formed of rubbery substance, more specifically, blend of NBR and ECO, were employed. They were 14 mm in external diameter. The ion conductive rollers were made different in the hardness and specific gravity of the elastic layer by varying them in ingredients, vulcanization condition, etc., although the hardness was kept within the range of 20° - 50°. More specifically, the amount by which sulfur was added, choice of filler, amount by which filler was added, and foaming condition, were varied to search for a desirable amount by which sulfur was to be added, desirable choice(s) of filler, a desirable amount by which filler was added, and a desirable foaming condition, for manufacturing a desirable ion conductive roller as a transfer roller.

25 First, the ratio by which sulfur was added to the rubber was varied to grasp the relationship between the amount of the sulfur in the elastic layer

and the amount of seepage (contamination). Generally, the greater the amount by which sulfur was added to the rubber, the higher the resultant cross-linking density, in other words, the harder the rubber became.

5 The results of the experiment in which the relationship between the amount by which sulfur was added to rubber and the extent of the contamination of the photosensitive drum 1 was examined by using a plurality of transfer rollers different in the amount
10 of the sulfur in the elastic layer thereof, being therefore different in the hardness of the elastic layer (rubber), are given in Table 1.

The ratio at which sulfur was added to the rubber was varied in the range of 0.5 phr to 2.0 phr
15 (ratio in weight of sulfur to rubber).

The plurality of transfer rollers comprised an aluminum core with an external diameter of 6 mm, and a cylindrical spongy elastic layer formed of the blend of NBR and ECO (blended at ratio of 8:2) and
20 fitted around the aluminum core so that the overall external diameter of the transfer roller became 14 mm. They were made different in the ratio of the sulfur in the elastic layer, being therefore different in the hardness of the elastic layer. Otherwise, they were
25 made the same in the other factors such as contents of the ingredients other than sulfur, conditions under which they were manufactured, etc.

roller was deduced from the extent of the contamination of a photosensitive drum by the seepage from the transfer roller.

The photosensitive drum and transfer roller
5 were kept pressed against each other with the application of pressure equivalent to 1,000 g of weight, and left unattended for one week in an environment that was 40°C in temperature and 95 % in humidity. After one week, the transfer rollers were
10 separated from photosensitive drums 1, and the area of each photosensitive drum, which was in contact with the photosensitive drum 1, was observed with the use of a microscope. In Table 1, "G" means that the photosensitive drum was contaminated, but the
15 contamination of the photosensitive drum 1 was not serious enough to suggest that the transfer roller should not be used for image formation; "E" means that the photosensitive drum 1 was in excellent condition; and "NG" means that the photosensitive drum 1 was
20 contaminated seriously enough to suggest that the usage of the photosensitive drum would result in the formation of a conspicuously defective image.

Table 1

25	S CONTENT	0.5 phr	1.0 phr	1.5 phr	2.0 phr
	CONTAMINATION	NG	G	E	E

E: excellent,

G: no problem in practical terms,

NG: contamination is serious enough to create problems.

5 The correlation between the method used for
testing the transfer rollers in the above described
experiment and the length of the actual service life
of a transfer roller had been established. In other
words, if a given roller was evaluated as E or G in
10 the above described test, it means that the roller
does not deteriorate in terms of image quality when
used as the transfer roller of an image forming
apparatus. On the other hand, if a given transfer
roller was evaluated as NG, it means that the roller
15 gradually deteriorates in terms of image quality while
it is used as the transfer roller of an image forming
apparatus.

 It is evident from Table 1 that the greater
the sulfur content of the elastic layer of a transfer
20 roller, in other words, the higher the cross-linking
density of the transfer roller, the harder the elastic
layer of the transfer roller, and the smaller the
amount by which the elastic layer ingredients with a
lower molecular weight seep out of the elastic layer
25 and contaminate a photosensitive drum.

(Amount of Filler)

Next, the abovementioned filler will be

described. The filler is added to the rubber for the purpose of improving the rubber in strength, processability, etc., making it easier for additives to be dispersed in the rubber, increasing the rubber
5 in apparent volume, or the like purposes. For example, inorganic substances such as carbon, calcium carbonate, or the like, are used as the filler.

It has been revealed by the studies made by the inventor of the present invention that the smaller
10 the amount of the inorganic filler in the elastic layer (rubber layer) of a transfer roller, the smaller the amount by which the elastic layer ingredients, such as the additives, seep out of the elastic layer and contaminate a photosensitive drum.

15 The results of the experiment in which a plurality of transfer rollers different in the amount of the filler in the elastic layer, were used to examine the relationship between the amount of the filler in the elastic layer of a transfer roller and
20 the extent of drum contamination are given in Table 2.

Each of the plurality of transfer rollers used in the experiment comprised an aluminum core with an external diameter of 6 mm, and a cylindrical spongy elastic layer formed of the blend of NBR and ECO
25 (blended at ratio of 8:2) and fitted around the aluminum core so that the overall external diameter of the transfer roller became 14 mm. The plurality of

transfer rollers were made virtually identical in specifications and manufacturing conditions, except for the ratio of the filler in the elastic layers (rubber layers) thereof to the rubber. The filler was
5 the half-and-half mixture of carbon black and calcium carbonate. The transfer rollers were made different in the weight ratio of the filler mixture to the rubber, within the range of 10 phr - 50 phr. They were subjected to the same test as the test which
10 yielded the results given in Table 1.

Table 2

15	FILLER CONTENT	10 phr	20 phr	30 phr	40 phr	50 phr
	CONTAMI- NATION	E	E	G	NG	NG

It is evident from the results given in Table
20 2 that the smaller the amount of the filler in the elastic layer of a transfer roller, the smaller the amount by which the ingredients with a low molecule weight in the elastic layer seep out and transfer onto a photosensitive drum. The filler is substantially
25 higher in specific gravity than rubber. Therefore, the greater the amount of the filler in the elastic layer material, the higher the specific gravity of the

elastic layer material.

Thus, as the means for controlling the specific gravity of the elastic layer of a transfer roller, it is effective to control the amount by which the filler is added to the material for the elastic layer. An elastic layer material which is higher in hardness and lower in specific gravity is lower in the amount of the filler therein, and therefore, is likely to be smaller in the amount of seepage. In other words, the higher the "hardness/specific gravity" ratio of the elastic layer of a transfer roller, the smaller the amount by which a photosensitive drum is contaminated by the seepage from the transfer roller.

Figure 6 shows the results of the evaluation, in terms of the photosensitive drum contamination, of the transfer rollers, different in the ingredients in the elastic layers thereof and vulcanization condition, obtained by repeating the same experiment as those carried out to obtain the results given in Tables 1 and 2.

The transfer rollers used in this experiment were the same as those used in the preceding experiments. In other words, they comprised an aluminum core with an external diameter of 6 mm, and a cylindrical spongy elastic layer formed of the blend of NBR and fitted around the aluminum core. Their overall external diameters were 14 mm. The transfer

rollers were made different in the hardness and specific gravity of the elastic layer by varying them in ingredients, vulcanization condition, etc., although the hardness was kept within the range of 20°
5 - 50°. The transfer rollers were evaluated using the same method as that used for evaluating the transfer rollers in the preceding experiments.

As will be evident from the graph in Figure 6, the distribution of the symbols representing the extent of the contamination of a photosensitive drum displays certain characteristics. That is, the
10 transfer rollers, the evaluations of which were in the top left area of the graph in Figure 6, in other words, the transfer rollers, which were no less than
15 65 in the "hardness/specific gravity", ratio were acceptable in terms of the extent of the contamination of the photosensitive drum. The results given in Figure 6 suggests that there is a correlation between the extent of the photosensitive drum contamination
20 and the "hardness/specific gravity" ratio of the elastic layer of a transfer roller. It is possible to grasp the extent of the seepage from a transfer roller, or the extent of the photosensitive drum contamination, from the results given Figure 6. In
25 other words, a numerical value 65 is the threshold value of "hardness/specific gravity" ratio.

As one of the means for preventing the

photosensitive drum contamination, it was proposed to expose the peripheral surface of a transfer roller to ultraviolet light or a beam of electrons, in order to prevent the seepage of the ingredients in the elastic layer of the transfer roller, by altering the surface properties of the transfer roller (Japanese Laid-open Patent Application 11-109770).

According to the description in Japanese Laid-open Patent Application 11-109770, the peripheral surface of the transfer roller is exposed to ultraviolet rays, a beam of electrons, or the like, in order to harden the surface portion of the transfer roller into a barrier layer, by triggering the cross-linking reaction in the surface portion of the transfer roller. It is assumed that the presence of the barrier layer prevents the peripheral surface of the transfer roller from reacting with the peripheral surface of a photosensitive drum, preventing thereby the ingredients of the elastic layer of the transfer roller from seeping out.

This method, however, had a problem in that as the surface layer of a transfer roller was hardened by the exposure to ultraviolet rays, the transfer roller was reduced in friction coefficient, becoming therefore slower in the speed at which the transfer roller conveyed transfer medium than a transfer roller which was not subject to ultraviolet rays. Further,

as the surface layer hardened by the exposure to ultraviolet rays was shaved, an unhardened layer was exposed, allowing thereby the ingredients of the elastic layer to seep out. Therefore, a transfer
5 roller, the surface layer of which was hardened by the exposure to ultraviolet rays or the like had to be replaced before the shaving of its surface layer became serious.

Further, exposing a transfer roller to
10 ultraviolet rays added to the number of the transfer roller manufacturing steps. Therefore, this solution proposed in Japanese Laid-open Patent Application 11-109770 was disadvantageous in terms of manufacturing time and equipment.

15 Thus, the primary object of the present invention is provide an electrically conductive roller, the ingredients of the elastic layer of which do not seep out; the peripheral surface of which does not change in friction coefficient regardless of the
20 frictional wear resulting from usage; and the surface layer of which does not constitutes a barrier layer.
[Theoretical Explanation of Contamination Prevention Mechanism]

An electrically conductive roller in
25 accordance with the present invention is higher in the cross-linking density of the spongy elastic (rubber) layer than an electrically conductive roller in

accordance with the prior art. It is characterized in that the entirety of the spongy elastic (rubber) layer is hardened. Therefore, the surface portion of its elastic layer does not need to be hardened into a
5 barrier layer in order to prevent the ingredients of its spongy surface layer from seeping out; it does not need to be exposed to ultraviolet rays or the like to increase it in cross-linking density to harden it. Further, in the case of the electrically conductive
10 roller in accordance with the present invention, the capability of preventing the seepage is not limited to the surface layer of the roller. In other words, the entirety of its elastic layer is capable of preventing the seepage. Therefore, even after the surface layer
15 becomes frictionally shaved due to usage, the ingredients in its elastic layer do not seep out from the fresh surface formed by the frictional shaving. The following is the theoretical explanation by the inventors of the present invention, regarding the
20 mechanism by which the seepage is prevented.

If a spongy elastic layer is higher in "hardness/specific gravity" ratio, it means that the wall portions, that is, the actual rubber portions, of the spongy elastic layer are strong. This means, from
25 the standpoint of physics, that the spongy elastic layer is smaller in the area by which it actually contacts an object. In other words, even if a spongy

elastic layer higher in "hardness/specific gravity" ratio, and a spongy elastic layer lower in "hardness/specific gravity" ratio are the same in the macroscopic size, that is, apparent size, of the contact area, or the nip, between an elastic layer and an object, the former is microscopically, that is, actually, smaller in the contact area. In other words, the former is smaller in terms of its contact with an object than the latter, and therefore, smaller in the amount of the chemical effects upon an object with which it comes into contact.

From the standpoint of chemistry, being larger in "hardness/specific gravity" ratio means being higher in cross-linking density. Being higher in cross-linking density means being more effective to keep contained the ingredients capable of seeping out. Moreover, being larger in "hardness/specific gravity" ratio means being smaller in the amount of the ingredients with a low molecular weight capable of seeping out in the first place. Further, the higher the cross-linking density, the stronger the tensile strength, and therefore, the smaller in the amount by which it is shaved. Therefore, being larger in "hardness/specific gravity" ratio is effective to prevent such contamination that results from the adhesion of minuscule shavings.

Because of the above described reasons, the

inventors of the present invention thought that the contamination of a photosensitive drum could be prevented by controlling the "hardness/specific gravity" ratio of a transfer roller.

5 [Conveyance of Transfer Medium]

The transfer roller in this embodiment does not contaminate a photosensitive drum even though the peripheral surface of its elastic layer is not hardened by a surface hardening process in which the
10 peripheral surface of the elastic layer is irradiated with ultraviolet rays or the like to be changed in cross-linking density. Thus, neither does it contaminate a photosensitive drum, nor change in transfer medium conveyance efficiency, even if the
15 interior of its elastic layer is exposed as the elastic layer is frictionally worn due to usage. Further, compared to a transfer roller which does not satisfy the inequality: $\text{hardness/specific gravity} \geq 65$, the transfer roller in this embodiment is smaller,
20 in the first place, in the amount by which the surface layer of its elastic layer is frictionally worn. Moreover, even among transfer rollers, the surface of which was not subjected to such a surface treatment as being irradiated with ultraviolet rays or the like,
25 the transfer roller in this embodiment displayed superior results; it was smaller in the changes in print magnification, that is, the changes in print

magnification ratio remained within the tolerable range throughout the guaranteed length of time (expected service life of an image forming apparatus).

5 The differences between the transfer roller in this embodiment irradiated with ultraviolet rays (which hereinafter may be referred to simply as UV), and the transfer roller in this embodiment unirradiated with ultraviolet rays, in terms of the changes in printing accuracy, which occurred as the
10 cumulative number of transfer mediums put through the image forming apparatus increased, are shown in Table 3.

 The image forming apparatus used for the experiment for testing these transfer rollers was 105
15 mm/sec in process speed, and was capable of outputting 15 letter size copies per minute. The guaranteed length of its service life was 50,000 copies. The amount of the pressure which was applied to keep the transfer roller upon the photosensitive drum was
20 equivalent to 500 g of weight.

Table 3

		PRINT MAG. CHANGE				
	HARDNESS/ SPECIFIC WEIGHT	AFTER 10000 SHEETS	AFTER 20000 SHEETS	AFTER 50000 SHEETS	AFTER 75000 SHEETS	
5	UV- TREATED	45	0.50%	0.80%	0.10%	0.12%
	NOT UV- TREATED	45	0.00%	-0.05%	-0.10%	-0.14%
10		67	0.00%	-0.01%	-0.03%	-0.04%

In the case of the transfer roller irradiated with ultraviolet rays, its hardened surface layer was frictionally worn, and the unhardened inner portion of its elastic layer, which was higher in friction coefficient, was exposed. Thus, it gradually increased in transfer medium conveyance efficiency, substantially reducing in printing accuracy. In comparison, in the case of the transfer roller which was unirradiated with ultraviolet rays, but was 45 in the value of "hardness/specific gravity" ratio, the amount by which it was frictionally worn through usage was substantial. Therefore, as the cumulative number of the transfer mediums increased, the efficiency with which the transfer medium, as an object to be moved, was conveyed by the unirradiated transfer roller which

was 45 in the "hardness/specific gravity" ratio, substantially reduced.

In comparison, in the case of the transfer roller unirradiated with ultraviolet rays and being 67
5 in "hardness/specific gravity" ratio, the amount by which it was frictionally shaved was smaller in the first place, being therefore excellent in performance.

To elucidate the aforementioned theory behind of the working mechanism of the transfer roller, an
10 elastic layer which is no less than 65 in "hardness/specific gravity" ratio is relatively high in cross-linking density, being therefore relatively high in tear strength. Therefore, it is less likely to tear, being therefore smaller in the amount by
15 which it is shaved.

As described above, according to this embodiment, by making the "hardness/specific gravity" ratio of the elastic layer of a transfer roller no less than 65 without subjecting the elastic layer to a
20 surface layer hardening process of irradiating it with ultraviolet rays or the like, it is possible to provide a transfer roller which does not contaminate a photosensitive drum, and is stable in transfer medium conveyance performance, throughout its service life.

25 Further, in the case of the electrically conductive roller in this embodiment, the entirety, instead of the surface layer, of its spongy elastic

layer is enabled to prevent the ingredients therein from seeping out. Therefore, even after the spongy elastic layer is frictionally shaved due to usage, it remains the same in surface friction coefficient.

5 Therefore, when it is used as a transfer roller for an image forming apparatus, it remains stable in transfer medium conveyance performance; it is preferable as a transfer roller for an image forming apparatus.

Further, by polishing in advance the
10 electrically conductive roller in this embodiment, it is possible to prevent the problem that there is a large amount of difference, in the surface properties of a transfer roller, between when the transfer roller is brand-new, and after it is substantially shaved by
15 transfer medium.

(Embodiment 2)

The second embodiment is the same as the first embodiment, except that the ratio of the sulfur and total amount of filler in the transfer roller in
20 the second embodiment is no less than 1.0 phr, and no more than 30 phr, respectively. The other specifications of the transfer roller in the second embodiment are the same as those in the first embodiment, and therefore, will not be described.

25 As will be evident from Tables 1 and 2, the greater the amount of sulfur in the elastic layer of a transfer roller, the smaller the amount of the seepage

therefrom. Further, the smaller the amount of the filler in the elastic layer of a transfer roller, the smaller the amount of the seepage therefrom.

In this embodiment, sulfur is added by no less than 1.0 phr, and the total amount of the filler is kept below 30 phr. Therefore, the transfer roller in this embodiment is highly effective in terms of solving the problem of photosensitive drum contamination.

The results of the experiment carried out to test the transfer rollers formed in accordance with the above described conditions regarding the sulfur and the total amount of filler, in order to confirm the effects of the sulfur contents and total amount of filler in the elastic layer of a transfer roller upon the drum contamination are given in Table 4.

The transfer rollers used for the experiment comprised an aluminum core with an external diameter of 6 mm, and a spongy elastic layer formed of the blend of NBR and ECO rubbers, on the peripheral surface of the aluminum core so that the overall diameter of the transfer roller becomes 14 mm. The test conditions are the same as those under which the results given in Table 1 were obtained.

Table 4

	EXAMPLE 1	EXAMPLE 2	EXAMPLE 3	
5	S CONTENT	1.0 phr	1.5 phr	2.0 phr
	CB (Filler) CONTENT	10 phr	10 phr	15 phr
	CaCO ₃ (Filler) CONTENT	20 phr	10 phr	0 phr
10	TRANSFER ROLLER HARDNESS (Asker-C)	33	32	31
	SPECIFIC WEIGHT OF ELASTIC LAYER	0.5	0.45	0.38
15	HARDNESS/ SPECIFIC WEIGHT	66	71	82
	DRUM CONTAMINATION	G	E	E

E: excellent

20 G: no problem in practical terms

NG: contamination is serious enough to create problems

25 As will be evident from Table 4, when sulfur was added by no less than 1.0 phr while the total amount of filler was kept at no more than 30 phr, the contamination of a photosensitive drum did not occur

even when the elastic layers of the transfer rollers were not irradiated with ultraviolet rays or the like. (Embodiment 3)

5 The third embodiment of the present invention is virtually the same as the first and second embodiments, except that only azodicarbonamide (which hereinafter will be abbreviated as ADCA) is used as the foaming agent for forming the spongy elastic layer of the transfer roller.

10 Azodicarbonamide as foaming agent is very high in foaming ratio, and therefore is needed by only a small amount to foam the rubber as the material for the elastic layer of a transfer roller. Therefore, azodicarbonamide is capable of providing a transfer
15 roller, the material for the elastic layer of which is high in cross-linking density, being therefore higher in hardness, and yet, the overall hardness of which is in the desirable range for the transfer roller for an image forming apparatus, more specifically, the range
20 of 20° - 50°.

Incidentally, it has been revealed that many of the additives to be added to the material for the elastic layer of a transfer roller are the sources of the seepage. In particular, the chemical compounds
25 resulting from the decomposition of foaming agent are likely to seep, being therefore likely to contaminate a photosensitive drum. However, the chemical

compounds resulting from the decomposition of azodicarbonamide are low in reactivity. Therefore, a spongy elastic (rubber) layer formed with the use of azodicarbonamide as foaming agent is much smaller in
5 the amount of the photosensitive drum contamination than a spongy elastic (rubber) layer formed with the use of foaming agent other than azodicarbonamide, for example, OBSH, etc.

The results of the drum contamination
10 experiment carried out to test the transfer rollers, the elastic layers of which were formed with the use of azodicarbonamide as foaming agent, are given in Table 5.

The transfer rollers used for the experiment
15 comprised an aluminum core with an external diameter of 6 mm, and a spongy elastic layer formed of the blend of NBR and ECO rubbers, on the peripheral surface of the aluminum core so that the overall diameter of the transfer roller became 14 mm. As the
20 foaming agent, VINIHOORU AC (commercial name of azodicarbonamide-series compound manufactured by EIWAKASEI, Co.) was used. The test conditions were the same as those under which the results given in Table 1 were obtained.

Table 5

	EXAMPLE 4	EXAMPLE 5
5	FORM MATERIAL CONTENT	ADCA 4 phr
	S CONTENT	2.0 phr
	CB (Filler) CONTENT	15 phr
10	CaCO ₃ (Filler) CONTENT	0 phr
	TRANSFER ROLLER HARDNESS (Asker-C)	31
15	SPECIFIC WEIGHT OF ELASTIC LAYER	0.38
	HARDNESS/ SPECIFIC WEIGHT	82
20	DRUM CONTAMINATION	E

E: excellent

G: no problem in practical terms

NG: contamination is serious enough to create
25 problems

As will be evident from Table 5, by using azocarbonamide-series compound as foaming agent, it was possible to produce transfer rollers which did not contaminate a photosensitive drum.

5 As described above, in this embodiment of the present invention, the solid portions of the spongy elastic layer of the transfer roller are increased in hardness by increasing them in cross-linking density. Therefore, the ingredients of the spongy elastic layer
10 can be prevented from seeping out of the elastic layer, without turning the surface portion of the elastic layer into a barrier layer by irradiating it with ultraviolet rays or the like.

Next, the usage of the above described ion
15 conductive rollers in an image forming apparatus, different from that in the preceding embodiments, will be described.

(Embodiment 4)

The "hardness/specific gravity" ratio of the
20 ion conductive rollers in this embodiment were no less than 65 as were those in the first to third embodiments. They were irradiated with ultraviolet rays, and tested using the image forming apparatus used to test the transfer rollers in the first
25 embodiment. These rollers in this embodiment did not suffer from the seepage problem even before they were irradiated with ultraviolet rays. Thus, they were

excellent as far as the seepage was concerned. Their performance in terms of transfer medium conveyance were as shown in Table 6. That is, among the irradiated transfer rollers transfer rollers, those
5 which were no less than 65 in the "hardness/specific gravity" ratio were better in that they were smaller in the change in print magnification. Further, they were better than the unirradiated transfer rollers, the "hardness/specific gravity" ratio of which was 45.
10 These results seem to have occurred for the following reason. That is, also in the case of the ion conductive rollers in this embodiment, as the surface portion of the roller irradiated with ultraviolet rays was shaved, it changed in friction coefficient, and
15 therefore, changed in the transfer medium conveyance performance, as did the transfer roller in the first embodiment. In the case of the ion conductive roller in this embodiment, however, the roller itself was difficult to shave in the first place. Therefore, the
20 changes in the friction coefficient which occurred as the portion having been hardened by being irradiated with ultraviolet rays was shaved were offset by the changes in the overall diameter of the roller, minimizing thereby the changes in the print
25 magnification resulting from the changes in the performance of the roller in terms of transfer medium conveyance.

Table 6

5	HARDNESS/ SPECIFIC WEIGHT	PRINT MAG. CHANGE			
		AFTER 10000 SHEETS	AFTER 20000 SHEETS	AFTER 50000 SHEETS	AFTER 75000 SHEETS
UV- TREATED	45	0.50%	0.80%	0.10%	0.12%
	67	0.04%	0.07%	0.03%	0.01%
10 NOT UV- TREATED	45	0.00%	-0.05%	-0.10%	-0.14%
	67	0.00%	-0.01%	-0.03%	-0.04%

15 In other words, from the standpoint of the
stability of the transfer medium conveyance
performance, the ion conductive rollers in this
embodiment were not as good as the ion conductive
roller in the first embodiment, but were better than
an ion conductive roller in accordance with the prior
20 art.

(Embodiment 5)

In this embodiment, the ion conductive
rollers which are the same in specification as those
in the preceding embodiments, and are manufactured
25 under the same conditions as those in the preceding
embodiments, are used as charge rollers. Their
electrical resistances measured in the normal

environment (20°C temperature and 60 % in humidity) after they were kept unattended for three days in the normal environment, were $10^6 \Omega$. The resistance was measured with the use of an apparatus shown in Figure 5 for measuring the electrical resistance of a roller; the charge roller 2 was placed where the transfer roller 5 is in Figure 5. To the aluminum cylinder, 500 V was applied. Incidentally, when the ion conductive roller in this embodiment is used as the charge roller for an image forming apparatus, the combination of a DC voltage of -600 V and an AC voltage which is 1,700 V in peak-to-peak voltage and is 1,000 Hz in frequency, is applied as charge bias to the charge roller, during image formation. The charge roller 2 is kept pressed on the photosensitive drum 1 with the application of a total pressure of 500 g.

The transfer rollers used for the experiment comprised an aluminum core with an external diameter of 6 mm, and a spongy elastic layer formed of the blend of NBR and ECO rubbers, on the peripheral surface of the aluminum core so that the overall diameter of the transfer roller became 14 mm. The charge roller 2 was kept in contact with the photosensitive drum 1 as an image bearing member, as were the transfer rollers in the preceding embodiments, so that the photosensitive drum 1 became charged as electrical discharge occurred between the

charge roller 2 and photosensitive drum 1, in the area which was slightly away from the contact area between the charge roller 2 and photosensitive drum 1, and in which there was a predetermined amount of gap between
5 the charge roller 2 and photosensitive drum 1. The charge roller 2 was rotationally supported in contact with the photosensitive drum 1 so that it would be rotated by the rotation of the photosensitive drum 1.

The charge roller 2 remained in contact with
10 the photosensitive drum 1 not only while it was rotated but also while it was kept stationary. If an ion conductive roller other than an ion conductive roller in accordance with the present invention is used as the charge roller of an image forming
15 apparatus, the photosensitive drum 1 is sometimes contaminated by the seepage from the charge roller, changing thereby the condition under which the photosensitive drum 1 is charged, which in turn reduces the performance of the image forming
20 apparatus. This symptom is particularly serious after the image forming apparatus is left unused for a long time, because while the image forming apparatus is left unused, a specific area of the charge roller 2 remains in contact with a specific area of the
25 photosensitive drum 1 for a long time.

In this embodiment, the ion conductive roller in accordance with the present invention is used as

the charge roller 2. Therefore, the above described photosensitive drum contamination does not occur.

Therefore, the cumulative length of time the photosensitive drum 1 can be uniformly charged to the normal potential level is much longer. Therefore, the
5 cumulative length of time the image forming apparatus remains normal in performance is longer.

(Embodiment 6)

Figure 7 is a drawing showing the sixth
10 embodiment of the present invention. Next, the sixth embodiment will be described with reference to the drawing.

Along the intermediary transfer belt 81 as a toner image bearing moving member, four image forming
15 stations are disposed in tandem. In each image formation station, an exposing apparatus, a charge roller, a developing apparatus, and a cleaning apparatus are disposed around the peripheral surface of the photosensitive drum.

20 The photosensitive drum 1a is 24 mm in diameter, and is charged by the charge roller 2a. The charged photosensitive drum 1a is exposed by the exposing apparatus 3a to form a latent image of a first color, or yellow color, on the peripheral
25 surface of the photosensitive drum 1a. The latent image on the photosensitive drum 1a is developed by the developing apparatus 4a which corresponds in

development color to the first color, or yellow. The developed yellow toner image is transferred onto the intermediary transfer belt 81 by the primary transfer roller 51a. Meanwhile, the formation of the toner
5 image of a second color, or magenta, begins in the second image forming station having the photosensitive drum 1b, so that the second color toner image will be layered on the yellow toner image on the intermediary transfer belt 81, in alignment therewith in term of
10 the direction perpendicular to the plane of the yellow toner image. The image formation on the photosensitive drum 1b is virtually the same as the above described formation of the toner image of the first color, or yellow. That is, the photosensitive
15 drum 1b is charged by the charge roller 2b. The charged photosensitive drum 1b is exposed by the exposing apparatus 3b to form a latent image of a second color, or magenta color, on the peripheral surface of the photosensitive drum 1b. The latent
20 image on the photosensitive drum 1b is developed by the developing apparatus 4b which corresponds in development color to the second color, or magenta. The developed magenta toner image is transferred onto the intermediary transfer belt 81 by the primary
25 transfer roller 51b, so that its position on the belt 81 coincides with the position of the toner image of the first color, or yellow. Similarly, the toner

image formed on the photosensitive drum 1c and the toner image formed on photosensitive drum 1d are transferred by the primary transfer rollers 51c and 51c, respectively, onto the intermediary transfer belt 81 so that the toner images are sequentially layered onto the preceding images, in alignment therewith. As a result, a full-color image is formed on the intermediary transfer belt 81.

As the full-color image is formed by layering in alignment the four monochromatic images different in color, a recording medium P is conveyed to the contact area between the secondary transfer roller 54 and intermediary transfer belt 81, and is conveyed through the contact area, in synchronism with the movement of the toner images on the intermediary transfer belt 81. As the recording medium P is conveyed through the contact area, the four color toner images on the intermediary transfer belt 81 are transferred all at once onto the recording medium P. Then, the four color toner images on the recording medium P are welded (fixed) to the recording medium by the head and pressure applied thereto by the fixing apparatus 6, yielding a permanent full-color image.

The toner particles remaining on the photosensitive drums 1a, 1b, 1c, and 1d after the primary transfer are removed by the cleaning apparatuses 7a, 7b, 7c, and 7d in the form of a blade,

respectively. The toner particles remaining on the intermediary transfer belt 81 after the secondary transfer are removed by the cleaning apparatus 71 also in the form of a blade.

5 The material for the intermediary transfer belt 81 is roughly 100 μ m thick film formed of polyimide resin, coated with fluoride. Its volume resistivity is in the range of $10^9 \Omega \cdot \text{cm}$ - $10^{10} \Omega \cdot \text{cm}$. The volume resistivity of the intermediary transfer
10 belt 81 was measured with the use of HAIRESTAA UP MCP-HT450 (product of Mitsubishi Petrochemical Co., Ltd.). The probe was UR-100, and the applied voltage was 1.0 kv. Instead of polyimide resin, multilayer film formed of one of the various rubbers, for
15 example, EPDM, NBR, Si, chloroprene rubber, hydrin rubber, etc., the volume resistivity of which are in the range of $10^4 \Omega \cdot \text{cm}$ - $10^9 \Omega \cdot \text{cm}$, and the thicknesses of which are in the range of 0.5 mm - 3 mm, may be used as the material for the intermediary transfer
20 belt 81. When one of these rubbers is used as the material for the substrate of the intermediary transfer belt 81, the substrate layer of the intermediary transfer belt 81 is to be reinforced by providing the substrate layer with a core having a
25 substantial amount of mechanical strength, and is to be coated with fluorinated resin or the like to provide the intermediary transfer belt 81 with a

surface layer, which is very high in electrical resistance, or dielectric, more specifically, a surface layer, which is 5 - 50 μm in thickness and no less than $10^{12} \Omega\cdot\text{cm}$ in volume resistivity.

5 As the primary transfer rollers 51a, 51b, 51c, and 51d, the ion conductive rollers in accordance with the present invention, the volume resistivities of which have been adjusted to the values in the range of $10^7 \Omega\cdot\text{cm}$ - $10^8 \Omega\cdot\text{cm}$ are used. As the secondary
10 transfer roller 52, the ion conductive rollers in accordance with the present invention, the volume resistivity of which has been adjusted to the values in the range of $10^8 \Omega\cdot\text{cm}$ - $10^9 \Omega\cdot\text{cm}$ is used.

 With the employment of these ion conductive
15 rollers in accordance with the present invention, it was possible to prevent the outward and inward surfaces of the intermediary transfer belt 81 from being contaminated. Therefore, the performance of the image forming apparatus could be kept stable in terms
20 of the primary and secondary transfers, for a long time.

 The primary transfer rollers 51a, 51b, 51c, and 51d comprised an aluminum core with an external diameter of 6 mm, and a spongy elastic layer formed of
25 the blend of NBR and ECO rubbers, on the peripheral surface of the aluminum core so that the overall diameter of the primary transfer roller became 14 mm.

They were kept in contact with the intermediary transfer belt 81 with the application of 500 g of pressure. If ion conductive rollers other than the ion conductive rollers in accordance with the present invention are used as the primary transfer rollers 51a, 51b, 51c, and 51d, it is possible that the surface of the intermediary transfer belt 81 will be so seriously contaminated, being thereby changed in transfer properties, by the seepage from the primary transfer rollers 51a, 51b, 51c, and 51d that the traces of the nips formed on the intermediary transfer belt 81 by the primary transfer rollers 51a, 51b, 51c, and 51d, and the intermediary transfer belt 81, can be recognized across the toner images transferred onto the intermediary transfer belt 81. More specifically, if ion conductive rollers other than the ion conductive rollers in accordance with the present invention are used as the primary transfer rollers 51a, 51b, 51c, and 51d, the ingredients having seeped out of the rollers 51a, 51b, 51c, and 51d form pieces of film, on the inward surface of the intermediary transfer belt 81, which affect the condition under which the intermediary transfer belt 81 is charged from the inward thereof. Further, the contamination, that is, film formation, on the inward surface of the intermediary transfer belt 81, affects the overall electrostatic capacity of the intermediary transfer

belt 81. Thus, in the advanced stage of the contamination on the inward surface of the intermediary transfer belt 81, the overall electrostatic capacity of the intermediary transfer belt 81 is substantially different from the initial electrostatic capacity of the intermediary transfer belt 81, affecting therefore the charging of the intermediary transfer belt 81 from the outward surface thereof as well.

10 As for the secondary transfer roller 52, it is placed in contact with the outward surface of the intermediary transfer belt 81 with the application of 1,000 g of pressure. In particular, in the case of the image forming apparatus in this embodiment, which is of the so-called tandem type, the secondary transfer roller 52 is always kept in contact with the intermediary transfer belt 81. In this embodiment, an ion conductive roller in accordance with the present invention is used as the secondary transfer roller 52. Therefore, there will be virtually no seepage from the secondary transfer roller onto the intermediary transfer belt 81. Therefore, the image forming apparatus in this embodiment can continuously forms images of good quality for a long time. If an ion conductive roller other than an ion conductive roller in accordance with the present invention is used as the secondary transfer roller 52, it is possible that

the ingredients of the secondary transfer roller 52 will seep out, and contaminate the outward surface of the intermediary transfer belt 81, changing thereby the condition under which the intermediary transfer belt 81 is charged from the outward surface side. Further, the contamination of the outward surface of the intermediary transfer belt 81 adversely affects the primary transfer processes in which the toner images are transferred onto the outward surface of the intermediary transfer belt 81 from the photosensitive drums 1a, 1b, 1c, and 1d as image bearing members. In other words, the contamination of the intermediary transfer belt 81 causes the settings of the transfer system to deviates from the optimal ones, that is, the original settings to which the transfer system has been initially set by design, which in turn results in the formation of inferior images.

In this embodiment, however, the problem that the intermediary transfer belt 81 is contaminated on both surfaces is prevented for a long period of time, making it possible to continuously obtain images of good quality for a long period of time. In addition, the employment of the ion conductive roller in accordance with the present invention, as the secondary transfer roller, which not only transfers images, but also conveys the transfer member, which is a moving member, makes the image forming stable in

terms of the transfer medium conveyance. Therefore,
when a toner image is transferred from a
photosensitive drum onto a transfer medium, the toner
image does not stretch or shrink, and the transfer
5 medium is not contaminated by the seepage from the
secondary transfer roller 52.

In this embodiment, the image forming
apparatus is provided with a plurality of image
forming station, and is structured so that a full-
10 color image can be completed while the intermediary
transfer belt 81 is rotated one full turn. However,
an ion conductive roller in accordance with the
present invention is also applicable to an image
forming apparatus structured so that the intermediary
15 transfer belt thereof are to be rotated plural number
of times to form a single full-color image.
Obviously, the length of time such an image forming
apparatus that employs an ion conductive roller in
accordance with the present invention as the secondary
20 transfer roller thereof can yield images of good
quality is substantially longer than the length of
time such an image forming apparatus that employs, as
the secondary transfer roller thereof, an ion
conductive roller other than an ion conductive roller
25 in accordance with the present invention. Such an
image forming apparatus must be structured so that the
secondary transfer roller 52 can be kept separated

from the cleaning apparatus 7 while the intermediary transfer belt 81 is rotated plural number of times to form a full-color image. However, there are still the opportunities for the secondary transfer roller 52 to
5 contact the intermediary transfer belt 81. Therefore, even in the case of such an image forming apparatus, the employment of an ion conductive roller in accordance with the present invention as a secondary transfer roller is beneficial from the standpoint of
10 preventing the contamination of the intermediary transfer belt 81.

(Embodiment 7)

Figure 8 is a drawing showing the seventh embodiment of the present invention. Next, the
15 seventh embodiment will be described with reference to the drawing.

Along the transfer medium conveyance belt 82 as a moving member, four image forming stations are placed in tandem. In each image formation station, an
20 exposing apparatus, a charge roller, a developing apparatus, and a cleaning apparatus are disposed around the peripheral surface of the photosensitive drum.

The photosensitive drum 1a is 24 mm in
25 diameter, and is charged by the charge roller 2a. The charged photosensitive drum 1a is exposed by the exposing apparatus 3a to form a latent image of a

first color, or yellow color on the peripheral surface of the photosensitive drum 1a. The latent image on the photosensitive drum 1a is developed by the developing apparatus 4a which corresponds in
5 development color to the first color, or yellow. The developed yellow toner image is transferred onto the transfer medium P on the transfer medium conveyance belt 82 by the primary transfer roller 53a. Meanwhile, the formation of the toner image of a
10 second color, or magenta, begins in the second image forming station having the photosensitive drum 1b, so that the second color toner image will be layered on the yellow toner image on the transfer medium P on the transfer medium conveyance belt 82, in alignment
15 therewith in term of the direction perpendicular to the plane of the yellow toner image. The image formation on the photosensitive drum 1b is virtually the same as the above described formation of the toner image of the first color, or yellow. That is, the
20 photosensitive drum 1b is charged by the charge roller 2b. The charged photosensitive drum 1b is exposed by the exposing apparatus 3b to form a latent image of a second color, or magenta color, on the peripheral surface of the photosensitive drum 1b. The latent
25 image on the photosensitive drum 1b is developed by the developing apparatus 4b which corresponds in development color to the second color, or magenta.

The developed magenta toner image is transferred onto the transfer medium P on the transfer medium conveyance belt 82 by the primary transfer roller 51b, so that its position on the transfer medium P on the belt 82 coincides with the position of the toner image of the first color, or yellow, on the transfer medium P on the belt 82. Similarly, the toner image formed on the photosensitive drum 1c and the toner image formed on photosensitive drum 1d are transferred by the primary transfer rollers 51c and 51d, respectively, so that the toner images are sequentially layered onto the preceding images on the transfer medium P on the transfer medium conveyance belt 82, in alignment therewith. As a result, a full-color image is formed on the transfer medium P on the transfer medium conveyance belt 82.

After the full-color image is formed on the transfer medium P by layering thereon in alignment the four monochromatic images different in color, the recording medium P is separated from the transfer medium conveyance belt 82, and is conveyed to the fixing apparatus 6, in which the four color toner images on the transfer medium P welded (fixed) to the transfer medium P, yielding a permanent full-color image.

The toner particles remaining on the photosensitive drums 1a, 1b, 1c, and 1d after the

primary transfer are removed by the cleaning
apparatuses 7a, 7b, 7c, and 7d in the form of a blade,
respectively. The fog causing toner particles having
been transferred onto the transfer medium conveyance
5 belt 82 are removed by the cleaning apparatus 71 also
in the form of a blade.

As the material for the transfer medium
conveyance belt 82, 50 μm - 200 μm thick film formed
of resinous substance such as PI, PVDF, ETFE, ABS,
10 polycarbonate, Nylon, etc., the electrical resistance
of which has been optimized, may be used. In the case
of the transfer medium conveyance belt 82 in this
embodiment, the surface resistivity is in the range of
 $10^7 \Omega/$ - $10^{12} \Omega/$, and the volumetric resistivity is
15 in the range of $10^7 \Omega\cdot\text{cm}$ - $10^{12} \Omega\cdot\text{cm}$. The surface and
volume resistivities of the transfer medium conveyance
belt 82 were measured with the use of HAIRESTAA UP
MCP-HT450 (product of Mitsubishi Petrochemical Co.,
Ltd.). The probe was UR-100, and the applied voltage
20 was 1.0 kv. Instead of the above listed resinous
substances, multilayer film formed of one of the
various rubbers, for example, EPDM, NBR, Si,
chloroprene rubber, hydrin rubber, etc., the volume
resistivity of which are in the range of $10^4 \Omega\cdot\text{cm}$ -
25 $10^9 \Omega\cdot\text{cm}$, and the thicknesses of which are in the
range of 0.5 mm - 3 mm, may be used as the material
for the transfer medium conveyance belt 82. When one

of these rubbers is used as the substrate layer of the transfer medium conveyance belt 82, the substrate layer of the transfer medium conveyance belt 82 is to be reinforced by providing the substrate layer with a
5 core having a substantial amount of mechanical strength, and is to be coated with fluorinated resin or the like to provide the transfer medium conveyance belt 82 with a surface layer, which is very high in electrical resistance, or dielectric, more
10 specifically, a surface layer, which is 5 - 40 μm in thickness, and no less than $10^{12} \Omega\cdot\text{cm}$ in volume resistivity.

In this embodiment, roughly 70 μm thick film formed of PI resin, the surface and volume
15 resistivities of which have been adjusted to roughly $10^9 \Omega/$ and $10^{10} \Omega\cdot\text{cm}$, respectively, was used as the material for the transfer medium conveyance belt 82.

As the primary transfer rollers 53a, 53b, 53c, and 53d, the ion conductive rollers in accordance
20 with the present invention, the volume resistivity of which had been adjusted so that their values fall within the range of $10^7 \Omega\cdot\text{cm}$ - $10^8 \Omega\cdot\text{cm}$ were employed.

With the employment of these ion conductive rollers in accordance with the present invention, it
25 was possible to prevent the inward surface of the transfer medium conveyance belt 82 from being contaminated. Therefore, the performance of the image

forming apparatus could be kept stable for a long time in terms of image transfer.

The transfer rollers 53a, 53b, 53c, and 53d are always kept in contact with the transfer medium conveyance belt 82 with the application of 500 g of pressure. If ion conductive rollers other than ion conductive rollers in accordance with the present invention are used as the transfer rollers 53a, 53b, 53c, and 53d, it is possible that the ingredients of the transfer rollers 53a, 53b, 53c, and 53d will seep out, and contaminate the inward surface of the transfer medium conveyance belt 82, changing thereby so seriously the condition under which toner images are transferred onto the transfer medium P on the transfer medium conveyance belt 82 that the traces of the nips formed between the transfer rollers 53a, 53b, 53c, and 53d and transfer medium conveyance roller 82 can be detected across the toner images formed on the surface of the transfer medium P on the transfer medium conveyance belt 82. The seepage from the ion conductive rollers, other than ion rollers in accordance with the present invention, used as the transfer rollers 53a, 53b, 53c, and 53d, form films on the inward surface of the transfer medium conveyance belt 82, and these films change the condition under which the transfer medium conveyance belt 82 is charged, in particular, from the inward side.

In this embodiment, however, ion conductive rollers in accordance with the present invention are employed as the transfer rollers 53a, 53b, 53c, and 53d. Therefore, the problem that the transfer medium
5 conveyance belt 82 is contaminated on both surfaces is kept under control for a long time, making it possible to produce images of good quality for a long time.

Although the present invention was described above with reference to the first to seventh
10 embodiments, these embodiments are not intended to limit the scope of the present invention. In other words, these applications are intended to cover such modifications or changes, for example, a multilayer roller or the like, as may come within the purposes of
15 the improvements or the scope of the following claims.

20

25